

Technical Data Sheet

P50GB-C40R

Copolymer Polypropylene Reinforced with Glass Fiber

Nirumand Polymer



Nirumand Polymer Co.
Filled & Reinforced Engineering Plastics

Product Description

P50GB-C40R is recycled copolymer polypropylene reinforced with 50% glass fiber. It provides good balance of toughness and stiffness, surface hardness, dimensional stability, good thermal and chemical resistance. This compound is used in automotive applications, home appliance industry, electrical goods, and other utility products. This grade is designed to be processed in conventional injection molding process.

General Properties

Material Status	•Commercial: Active
Forms	•Pellets
Processing Method	•Injection molding
Color	•Black

Physical Properties	Value	Unit	Test Method
Density	1.33	gr/cm ³	ISO 1183
Melt Mass-flow Rate (MFR) (230°C/2.16 kg)	gr/10 min	ASTM D1238
Shrinkage	< 0.1	%	Internal

Mechanical Properties	Value	Unit	Test Method
Tensile Strength@Break	67	MPa	ISO 527
Elongation @ Break	6	%	ISO 527
Flexural Modulus	8000	MPa	ASTM D790

Impact	Value	Unit	Test Method
Notched Izod Impact (23°C)	≥ 8	kJ/m ²	ISO 180
Notched charpy Impact (23°C)	kJ/m ²	ISO 180

Hardness	Value	Unit	Test Method
Durometer Hardness	72	Shore D	ASTM D2240

◆ Values shown are average & are not to be considered as product specifications.

Web-site: www.npolymer.com
Address: Abbas abad Industrial Zone-Tehran-Iran

E-mail: Sales@npolymer.com, Trade@npolymer.com
Tel & Fax: (+9821)35000234